



# Composite Material of Clay-biochar for Cadmium Ion Removal from Water

Mohamed Hussein Omar <sup>a\*</sup>, Njagi Njomo <sup>a</sup>, Amir O. Yusuf <sup>a</sup>  
and Immaculate Michira <sup>a</sup>

<sup>a</sup> Department of Chemistry, University of Nairobi, P.O. Box 30197, GPO, Nairobi, Kenya.

## Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

## Article Information

DOI: 10.9734/AJACR/2023/v14i1256

## Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/102383>

Original Research Article

Received: 25/04/2023  
Accepted: 27/06/2023  
Published: 04/07/2023

## ABSTRACT

A research study of the synthesis of nanocomposite of clay-biochar material acquired from normal clay and biomaterial of *Prosopis Juliflora* for cadmium ion removal from aqueous solutions is reported. Composite materials were prepared by heating of ordinary clay and biomaterial of *Prosopis* at 500°C temperature and the synthesis was established with XRF, EDX, FTIR, XRD and SEM characterization. The results of characterized material showed that clay minerals successfully permeated the surface of biochar materials to form composites. The effectiveness of the composites in removing cadmium metal was determined by a batch adsorption procedure. The composite material produced a removal efficiency of 99% of cadmium ions. Adsorption was investigated using the adsorption isotherms of Freundlich and Langmuir which showed correlation  $r^2$  values of 0.924 and 0.932 respectively for the removal of cadmium ions from water. The results also revealed a pseudo second-order reaction for cadmium ions removal.

**Keywords:** Clay-biochar; composite material; cadmium; adsorption.

\*Corresponding author: Email: [mhussein2630@gmail.com](mailto:mhussein2630@gmail.com);

## 1. INTRODUCTION

Water as a commodity is essential for humans and other living organisms. Clean drinking water is a basic requirement for good health. On 28 July 2010, the United Nations General Assembly documented the rights of animals to water and sanitation through resolution 64/292. The resolution recognizes that clean drinking water is essential for the realization of human rights and calls on states and international organizations to provide clean, affordable and accessible drinking water and sanitation for all [1]. However, in certain environments, anthropogenic activities associated with mining and various industrial uses can naturally exceed guidelines for water quality and safe drinking water [2]. Heavy metals such as Cr, Cu, Ni, Zn, Pb, Cd, and Hg, are a major concern because of their toxicity and persistence in the environment [3]. Heavy metal contamination of water poses particular risks to humans and animals due to bioaccumulation in food chain [4]. Inhalation of high levels and prolonged interactive contact with cadmium oxide vapours can lead to acute pneumonia with pulmonary edema, which in severe cases can be fatal [5]. The main target organs in the body where this metal is toxic are the lungs, kidneys and bones [6]. The maximum permissible level of cadmium in drinking water is 0.005 mg/L according to USEPA, EU and KEBS and 0.01 mg/L according to NEMA standards.

Environmental pollution of water is a major threat, and researchers are interested in developing inexpensive and effective techniques for the removal of heavy metals from various environmental matrices. The use of nanotechnology and nanocomposites in the treatment of waste water has gained traction of researchers with advances in fiber, metal nanoparticles, nanophotocatalyst, nano membranes and heterojunction nanomaterials as the latest trends [7]. The use of clay as adsorbent is novel since it is available natural and at a low cost [8]. Many studies have shown that biochar is important in improving soil properties and increasing crop yields [9, 10, 11]. Biochar and its activated derivatives remove various contaminants, including pathogens [12–15], inorganic substances such as heavy metals [16,17], and organic impurities such as dyes [18,19], due to their improved properties such as high carbon content, larger surface area, high cation/anion exchange capacity, and stable structure [20]. The use of biochar and its modification using acid oxidation increases the

functional groups of biochar cation exchange capacity, micropores, specific surface area and oxygen content [21]. The use of biochar as a safe, potential low-cost and sustainable technology for treatment of wastewater has been reported, although its technological use has been constrained by lack of design information and environmental public health risk constrains. Largely untapped opportunity is to convert agricultural wastes (such as crop residues) from system of production into biochar by pyrolysis and its use for water treatment [22]. However, the use of biochar from *Prosopis Juliflora* has not been exhausted to remove contaminants especially heavy metals. *Prosopis Juliflora* plant is an invasive plant that has taken over rangelands in arid and semi-arid which is becoming a menace to both farmers and pastoralist in the world. Proper use and management of the *Prosopis* will be a blessing to those affected by its spread [23] especially in the arid and semi-arid region of Kenya. In this study clay-biochar nanocomposite materials were synthesized and tested for their adsorption of cadmium ions in aqueous media. The novelty is in the use of locally available clay and biochar from invasive species of *Prosopis* that will help in the containment of its spread for proper management and use.


## 2. MATERIALS AND METHODS

### 2.1 Study Area and Sampling


The ordinary clay was picked up from the Kimathi Valley, Mukurweini sub-county, Nyeri County (0°37'55.9" S, 37°9'43.8" E). Sampling of *Prosopis Juliflora* was carried out on the edges of Tana River in Garissa County (0° 27' 50" S, 39° 38' 12' 'E. Fig. 1 and Fig. 2 shows the study research areas from where sample materials were collected.

### 2.2 Experimental Procedure

The collected clay was pre-treated to eliminate impurities. The fresh clay was washed with a sufficient amount of deionized water, stored for 24 hours, decanted until the decanted water was completely clear, and then air dried. The dried clay was then ground and sieved. Calcination of the clay was performed at 1000°C for 1 hour using a furnace (Daihan FHX, Digital Muffle Furnace, Standard Type, 1200°C, FHX-03/05/12/14/27/63). The small portions of *Prosopis* were dried, ground and the ground powder were dried in the air 24 hrs to decrease



**Fig. 1. Sampling area in Mukurweini, Nyeri County**



**Fig. 2. Sampling area in Garissa township, Garissa County**

the amount of moisture. The pyrolysis of *Prosopis* and calcined clay to form composite was performed using the same furnace at 500°C. In general, as the temperature of biochar production increases, so does the pH value of the resulting biochar. Oxygen-containing acidic functional groups that contribute to the acidity of biochar at low temperatures loses oxygen at high temperatures, increasing the pH of biochar as the pyrolysis temperature increases [24]. The calcined clay and biomaterial were pyrolyzed in a 1:1 ratio to form the composite material at 500°C temperature for 2 hours. At the start, the same amount of calcined clay and biochar was used in each case, then different ratios were used to achieve the optimum dispersion for impregnation. However, researchers report that for equal

dispersion of the two materials to be achieved the equal amount is the recommended dosage for mixing of the two materials [25]. After the pyrolysis process, the oven was left for a while to cool to room temperature. Nanocomposite materials were characterized with Fourier-transform infrared spectroscopy (FTIR), Transmission electron microscopy (TEM) (JEM-2100F), Scanning electron microscopy (SEM) (model; Quatro S), XRF, EDX, and X-ray Powder Diffraction (XRD) (Rigaku powder XRD model Ultima IV, conditions: start angle 5, stop angle 70, scan speed 5). Analysis of the nanocomposite materials elemental composition was performed using X-ray fluorescence (XRF) and Energy Dispersive X-Ray Analysis (EDX). XRD of the composite was done to decide the

phase analysis. Morphological studies and size measurement were performed by FESEM and TEM. In the FTIR investigation, pellets were prepared using potassium bromide (KBr). A batch adsorption technique was used to examine the efficiency of cadmium removal by nanocomposite material. Mixed standards of heavy metals that contains cadmium (1000 mg/L) was put in a 1-liter flask to accomplish a 1 mg/L concentration of cadmium ion. A 25 mL of cadmium ion diluted solution was placed in a flask and the suitable dose (1, 2, 4 and 6 mg) of nanocomposite was added while keeping the rest of the parameters constant (contact time, agitation speed, and pH) i.e. 120 min, 150 rpm, and pH-8 respectively. pH adjustments were made with HCl or NaOH (dilute) to reach the required pH. Removal efficiency was achieved using Equation 1 established on the reduced concentration of cadmium for each sample.

$$\% \text{ efficiency of removal} = \frac{(C_i - C_f) \times 100}{C_i} \quad (1)$$

Where  $C_i$  is the original metal ion (mg/L) concentration and  $C_f$  is the metal ion equilibrium concentration after the adsorption process (mg/L).

### 3. RESULTS AND DISCUSSION

Elemental analysis by EDX indicated that the composition of the nanocomposites was rich in C, O, Si, Al, and Fe. Carbon originated from biochar while the other elements emanated from clay. The content was 49.05% C, 35.85% O, 5.7% Si, 5.2% Al and 2.05% Fe as shown in Fig. 3 (A) and (B).

The FTIR spectrum of the nanocomposite material presented a broad peak at around  $3645 \text{ cm}^{-1}$  and  $2349 \text{ cm}^{-1}$ , which is symbolic of O-H stretching and  $\text{CO}_2$  absorption respectively. The peak at  $1063 \text{ cm}^{-1}$  was assigned to the vibration of C-O stretching. Therefore, it indicated that the material of the biochar content was contained well in the nanocomposite, indicating the effective clay content impregnation onto the biochar surface as shown in Fig. 4.




Fig. 3. Patterns/Images of composite material duplicate (A) and (B) using EDX (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)






Fig. 4. FTIR spectrum of nanocomposite material (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)

XRD of the nanocomposite revealed the presence of mineral crystals, as shown in Fig. 5. In the image, three (3) peaks appearing at  $19.9^{\circ}$ ,  $25^{\circ}$  and  $35^{\circ}$  were recognized as expandable phyllosilicates [26]. These XRD results were in good agreement with the results of EDX, indicating that the process of pyrolysis effectively impregnated clay minerals onto the surface of the biochar to produce clay-biochar composite material.


Fig. 6 and Fig. 7 shows images of SEM of the clay-biochar composite. They indicated that the surface of the sample was largely covered with a thin film structure exhibiting a layered surface, and also exhibited a distinct morphology typical of clay, indicating an impregnation success of content of the clay minerals on the biochar surface as confirmed by EDX analysis as showed in Fig. 8.




**Fig. 5. XRD pattern of clay-biochar nanocomposite (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)**



**Fig. 6. SEM images of nanocomposite at 100 μm (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)**




**Fig. 7. SEM images of nanocomposite X5 at 20 μm (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)**




**Fig. 8. EDX spectrum of the nanocomposite (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)**

The following parameters were considered for the batch sorption analysis; pH, contact time, shaker speed, material dosage, and optimization of each of them [27]. The removal efficiency of the nanocomposite material for cadmium ions from water was 99.5% as shown in Fig. 9. For the Freundlich isotherm sorption data, the  $r^2$  fit for the composite was 0.924 and the  $r^2$  fit for the

Langmuir isotherm sorbent composite was 0.932, as shown in Figs. 10 and 11, respectively. Experiments of Kinetics indicated that the second order model close-fitting the data better than the first order model, as shown in Fig. 12. The second-order model showed a linear fit, but the pseudo first-order model did not.



**Fig. 9. Removal efficacy of composite material of Cd ions (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc = 1ppm)**



**Fig. 10. Freundlich isotherms for composite material demonstrating trends in cadmium ion adsorption (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)**




Fig. 11. Langmuir isotherm for composite material demonstrating trends in cadmium ion adsorption (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)




Fig. 12. Plot of Pseudo First and second order models of cadmium ion (pH=8, shaker speed=150 rpm, Contact time=120 min, Cd conc= 1ppm)

#### 4. CONCLUSION

This research study focused on the synthesis of a clay biomaterial composite of *Prosopis* for the removal of cadmium ions from water. The composites were developed by calcining the clay and biomaterials at a temperature of 500 °C, and the synthesis of the nanocomposites was determined by XRF, EDX, FTIR, XRD and SEM characterization techniques. Analysis of the characterized material showed that the surface of the biochar was impregnated with clay mineral crystals to produce a composite material. A batch adsorption process was used to study the removal efficiency of cadmium ions by the composite. The composite material has shown remarkable efficiency in removing cadmium ions from water. Freundlich and Langmuir isotherms were used to study the adsorption of cadmium ions. Both showed good suitability for removing cadmium ions. The results also established a pseudo-model for secondary reactions to remove cadmium ions.

#### ACKNOWLEDGEMENTS

We thank the National Research Fund (NRF-Kenya) for the support of the project financially.

#### COMPETING INTERESTS

Authors have declared that no competing interests exist.

#### REFERENCES

1. Assembly, U. G., The Human Rights to Water and Sanitation. Equality in Water and Sanitation Services. 2010; 1249(20378):26–43.
2. Komkiene J, Baltreinaite E. Biochar as adsorbent for removal of heavy metal ions [Cadmium (II), Copper (II), Lead (II), Zinc (II)] from aqueous phase. International Journal of Environmental Science and Technology. 2016;13:471-82.

3. Inyang, Mandu I, Bin Gao, Ying Yao, Yingwen Xue, Andrew Zimmerman, et al.. A review of biochar as a low-cost adsorbent for aqueous heavy metal removal. *Critical Reviews in Environmental Science and Technology*. 2016;46(4):406-433.
4. Obinna IB, Ebere EC. A review: Water pollution by heavy metal and organic pollutants: Brief review of sources, effects and progress on remediation with aquatic plants. *Analytical Methods in Environmental Chemistry Journal*. 2019; 2(03):5-38.
5. Sharma VK, Sohn M. Aquatic arsenic: Toxicity, speciation, transformations, and remediation. *Environment international*. 2009;35(4):743-59.
6. Engwa GA, Ferdinand PU, Nwalo FN, Unachukwu MN. Mechanism and health effects of heavy metal toxicity in humans. *Poisoning in the Modern World-New Tricks for an Old Dog*. 2019;10:70-90.
7. Mehta, Komal P, Rajneesh Sharma, Shubhajit Haldar, Atul Kumar. Advancement in treatment of wastewater with nano technology. *Materials Today: Proceedings*. 2023;80:3358-3362.
8. Srinivasan R. Advances in application of natural clay and its composites in removal of biological, organic, and inorganic contaminants from drinking water. *Advances in Materials Science and Engineering*; 2011. Available:<https://doi.org/10.1155/2011/872531>
9. Windeatt Jayne H, Andrew B Ross, Paul T Williams, Piers M Forster, Mohamad A Nahil, et al. Characteristics of biochars from crop residues: Potential for carbon sequestration and soil amendment. *Journal of Environmental Management*. 2014;146:189-197.
10. Agegnehu, Getachew, Anoop Kumar Srivastava, Michael I Bird. The role of biochar and biochar-compost in improving soil quality and crop performance: A review. *Applied soil Ecology*. 2017;119:156-170.
11. Yu, Haowei, Weixin Zou, Jianjun Chen, Hao Chen, Zebin Yu, et al. Biochar amendment improves crop production in problem soils: A review. *Journal of Environmental Management*. 2019;232:8-21.
12. Reddy Krishna R, Tao Xie, Sara Dastgheibi. Evaluation of biochar as a potential filter media for the removal of mixed contaminants from urban storm water runoff. *Journal of Environmental Engineering*. 2014;140(12):04014043.
13. Molaei R. Pathogen and Indicator Organisms Removal in Artificial Greywater Subjected to Aerobic Treatment. Master's Thesis, Department of Energy and Technology, The Swedish University of Agricultural Science in Uppsala, Uppsala, Sweden; February 2014.
14. Kaetzl, Korbinian, Manfred Lübken, Tito Gehring, Marc Wichern. Efficient low-cost anaerobic treatment of wastewater using biochar and woodchip filters. *Water*. 2018;10(7):818.
15. Kaetzl K, Lübken M, Nettmann E, Krimmler S, Wichern M. Slow sand filtration of raw wastewater using biochar as an alternative filtration media. *Sci. Rep.* 2020;10: 1229.
16. Yang W, Wang Z, Song S, Han J, Chen H, Wang X, et al. Adsorption of copper(II) and lead(II) from seawater using hydrothermal biochar derived from *Enteromorpha*. *Mar. Pollut. Bull.* 2019;149:110586.
17. Gwenzi W, Musarurwa T, Nyamugafata P, Chaukura N, Chaparadza A, Mbera S. Adsorption of Zn<sup>2+</sup> and Ni<sup>2+</sup> in a binary aqueous solution by biosorbents derived from sawdust and water hyacinth (*Eichhornia crassipes*). *Water Sci. Technol.* 2014;70:1419–1427
18. Chen Y, Lin YC, Ho SH, Zhouc Y, Ren N. Highly efficient adsorption of dyes by biochar derived from pigments-extracted macroalgae pyrolyzed at different temperature. *Bioresour. Technol.* 2018; 259:104–110
19. Park JH, Wang JJ, Meng Y, Wei Z, DeLaune RD, Seo DC. Adsorption/desorption behavior of cationic and anionic dyes by biochars prepared at normal and high pyrolysis temperatures. *Colloids Surf. A Physicochem. Eng. Asp.* 2019;572:274–282.
20. Rizwan Muhammad, Shafaqat Ali, Muhammad Farooq Qayyum, Muhammad Ibrahim, Muhammad Zia-ur-Rehman, Tahir Abbas, et al. Mechanisms of biochar-mediated alleviation of toxicity of trace elements in plants: A critical review. *Environmental Science and Pollution Research*. 2016;23:2230-2248.
21. Gope, Manash, Rajnarayan Saha. Removal of heavy metals from industrial effluents by using biochar. In *Intelligent*

- Environmental Data Monitoring for Pollution Management. 2021;25-48 (Academic Press).
22. Gwenzi W, Chaukura N, Noubactep C, Mukome FN. Biochar-based water treatment systems as a potential low-cost and sustainable technology for clean water provision. Journal of Environmental Management. 2017;197:732-749.
  23. Huho, Julius M, Mohamed Hussein Omar. Prosopis juliflora in Asals of Kenya: A friend or a foe plant. Int. J. Sci. Res. 2020;Publ 10:9968.
  24. Rehra D, Reddy MR, Novak JM, Bansode RR, Keith A, Schimmel, Jianmei Yu, D, et al. Production and characterization of biochars from agricultural by-products for use in soil quality enhancement. Journal of Analytical and Applied Pyrolysis. 2014;108:301-309.
  25. Rallet, Danga, Abba Paltahé, Cornelius Tsamo, Benoît Loura. Synthesis of clay-biochar composite for glyphosate removal from aqueous solution. Heliyon. 2022; 8(3):e09112.
  26. Yao Y, Gao B, Inyang M, Zimmerman AR, Cao X, Pullammanappallil P, et al. Biochar derived from anaerobically digested sugar beet tailings: Characterization and phosphate removal potential. Bioresource Technology. 2011;102(10):6273-8.
  27. Rediske NM. The characterization of the adsorption of cadmium from aqueous solution using natural fibres treated with nanoparticles. Montana Tech of the University of Montana; 2014.

© 2023 Omar et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

*Peer-review history:*

*The peer review history for this paper can be accessed here:*  
<https://www.sdiarticle5.com/review-history/102383>